

## EnviroTuf 22

**Reinforced Composite TPO Sheet** 

## **Product Description**

EnviroTuf 22 is a composite sheet that utilizes short-strand fiberglass to reinforce the base resin. It can be used in thermoforming applications to replace traditional chopped-strand or closed-mold fiberglass parts and is available as UV stabilized for outdoor protection.

## **Technical Properties**

Property	Test Method	Value*
Specific Gravity	ASTM D-792	1.03
Tensile Strength	ASTM D-638	8,500 psi
Flexural Modulus secant	ASTM D-790	512,000 psi
Flexural Modulus tangent	ASTM D-790	700,000 psi
Izod Impact (Notched) 23°C	ASTM D-256	5.2 ft-lbs/in
Izod Impact (Notched) -20°C	ASTM D-256	2.0 ft-lbs/in
Instrumented Impact - Total Energy at 72°F	ASTM D-3763	43 ft-lbs
Instrumented Impact - Total Energy at -30°C	ASTM D-3763	37 ft-lbs
Heat Deflection Temperature (@66 psi)	ASTM D-648	300°F
Heat Deflection Temperature (@264 psi)	ASTM D-648	235°F
Coefficient of Linear Thermal Expansion	ASTM D-696	2.5x10 <sup>-5</sup> in/in/°F
Coefficient of Linear Thermal Expansion	ASTM D-696	3.5x10 <sup>-5</sup> in/in/°F
Mold Shrinkage (extrusion direction)	Internal	0.005-0.009 in/in
Mold Shrinkage (transverse direction)	Internal	0.015-0.018 in/in
Flammability	UL 94-HB	Passes at 0.60"
Flammability	FMVSS 302 *All values based on 0.125"	Passes at 0.60"

\*All values based on 0.125' unless otherwise stated

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.