

Extreme LG

Low Gloss TPO Sheet

Product Description

Extreme LG is a low gloss, high performance thermoplastic polyolefin (TPO) sheet engineered for improved thermoforming characteristics. Extreme LG provides a wide processing range, enabling consistent, controlled sag performance for stable thermoforming. For OEM's, Extreme LG provides excellent cold crack resistance, outstanding chemical resistance, and a medium to low gloss molded-incolor surface. Along with an improved processing window, Extreme LG provides the most cost-effective TPO in the marketplace for large part thermoforming applications.

Technical Properties

Property	Test Method	Value*
Specific Gravity	ASTM D-792	1.08-1.13
Tensile Strength	ASTM D-638	3,100 psi
Flexural Modulus	ASTM D-790	270,000 psi
Flexural Strength	ASTM D-790	9,600 psi
Izod Impact (Notched) 72°F	ASTM D-256	6.5 ft-lbs/in
Heat Deflection Temperature (@66 psi)	ASTM D-648	240°F
Coefficient of Linear Thermal Expansion	ASTM D-696	2.2x10 ⁻⁵ in/in/°C
Gardner Gloss (High Gloss, Smooth Sheet)	ASTM D-523	25 - 30 Gloss Units-60°
Flammability	UL 94-HB	Passes at 0.60"
Flammability	FMVSS 302	Passes at 0.60"

*All values based on 0.125" unless otherwise stated

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com or visit our website

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.