

HIPS GP Print Grade

High Impact Polystyrene GP Print Grade

Product Description

High impact polystyrene (HIPS) is one of the most versatile thermoplastic materials. Widely used in a variety of applications, HIPS can be formed, die-cut, fabricated and printed. Specially formulated and rubber modified, HIPS provides a superior surface texture and excellent ink adhesion characteristics needed for a variety of print methods. With the ability to easily adjust opacities, dyne levels and hues, it is commonly used in digital, screen and offset printing applications.

Technical Properties

Property	Test Method	Value
Specific Gravity	ASTM D-792	1.10*
Rockwell Hardness (R Scale)	ASTM D-785	72
Tensile Strength yield	ASTM D-638	3,300 psi
Flexural Strength	ASTM D-790	4,800 psi
Flexural modulus	ASTM D-790	325,000 psi
Multiaxial Impact	ASTM D-3763	1.9 ft lbf
Vicat Softening Point	ASTM D-1525	210°F
Gardner Gloss	ASTM D-523	15% -60°

- * Opacity dependent
- All values based on 0.028" unless otherwise stated

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**