

## Royalite® HG

Holster Grade sheet

## **Product Description**

Royalite Holster Grade thermoplastic sheet provides a rigid acrylic/PVC product that combines very high impact strength, tensile strength, stiffness and hardness with excellent formability. Royalite Holster Grade sheet has excellent chemical and stain resistance. Royalite Holster Grade is available in a wide variety of standard and custom colors, grain textures, gauge and blank sizes subject to normal production scheduling.

## **Technical Properties**

Property	Test Method	Value*
Specific Gravity (color dependent)	ASTM D-792	1.35
Tensile Strength	ASTM D-638	5,800 psi
Flexural Strength	ASTM D-790	9,500 psi
Flexural Modulus	ASTM D-790	320,000 psi
Izod Impact (Notched) 72°F	ASTM D-256	15.0 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	100
Heat Deflection Temperature (@264 psi -		
annealed)	ASTM D-648	150°F
Thermal Conductivity	ASTM C-177	1.01 BTU/in/hr/ft2/°F
Coefficient of Linear Thermal Expansion	ASTM D-696	4.0 - 6.0x10-5 in/in/°F

<sup>\*</sup>All values based on 0.125" unless otherwise stated and no use of customer regrind

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail <a href="mailto:info@spartech.com">info@spartech.com</a> or visit our website at <a href="https://www.spartech.com">www.spartech.com</a> or visit our website

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.