

SurfaceChoice[™] Realtree Xtra®Korad® over TPR-1 Flexible Sheet

Product Description

TPR Blend 1 a custom solution for automotive panels and parts. Our specialty formulated sheet incorporates 25 years of experience in the North American automotive markets. TPR Blend 1's advanced characteristics provide a durable, formable solution to meet customer needs. The Realtree Xtra[®] Korad[®] overlay combines the TPR characteristics with the weather resistant features of Korad[®] film.

Technical Properties

Property	Test Method	Value*
Specific Gravity (color dependent)	ASTM D-792	0.98
Tensile Strength, MD	ASTM D-412	1200 psi
Tensile Strength, TD	ASTM D-412	1000 psi
Ultimate Elongation, MD	ASTM D-412	920%
Ultimate Elongation, TD	ASTM D-412	600%
Flexural Modulus	ASTM D-790	19,000 psi

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail <u>info@spartech.com</u> or visit our website at <u>www.spartech.com</u>

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.