

TPR-5 Preliminary

Flexible Sheet

Product Description

TPR Blend 5 a custom solution for automotive panels and parts. Our specialty formulated sheet incorporates 25 years of experience in the North American automotive markets. TPR Blend 5's advanced characteristics provide a durable, formable solution to meet customer needs.

Technical Properties

Property	Test Method	Value
Specific Gravity	ASTM D-792	0.94
Hardness - Shore D	ASTM D-2240	54
Tensile Strength	ASTM D-638	MD 2,000 psi
Tensile Elongation at Break	ASTM D-412	MD 1,100%

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail <u>info@spartech.com</u> or visit our website at <u>www.spartech.com</u>

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.